

REC GROUT 747

Highly fluid non-shrink cementitious grout

PRODUCT

Rec Grout 747 is a ready- to-use free flow precision grout made of sand, special cement and additives to provide an outstanding performance in terms of volume stability, flow, and physical properties.

SCOPE OF USE

- Filling of shutter tie rod openings
- Void filling applications
- Concrete re-profiling
- Anchoring of tie bar and bolts
- Pile top re-profiling
- Base plates

ADVANTAGES

- Highly fluid
- Chloride & Hydrogen free
- High early mechanical resistance
- Good resistance to chlorides and sulfates
- Easy application
- Excellent resistant to vibration and shock loads
- Pumpable
- High dense
- Low permeability

CHARACTERISTICS	
Appearance	Grey powder
Grain size	0 to 1 mm
Wet density (kg/m ³)	2.15 - 2.25
Mixing water	17% - 18% (4.25-4.5 Lit water per 25 Kg powder)
Initial Setting time (min)	255
Final Setting time (min)	355
Free from chlorides and metallic particles	

APPLICABLE STANDARDS

BS EN 196-1
BS EN 12190
EN 12190
BS EN 12390-3

*COMPRESSIVE STRENGTH (N/mm ²)			
AGE	1 day	7 days	28 days
COMPRESSIVE STRENGTH (N/mm ²)	>25	>45	>60
Standard	BS EN 12390-3	BS EN 12390-3	BS EN 12390-3

REC GROUT 747

*FLEXURAL STRENGTH		
AGE	7 days	28 days
FLEXURAL STRENGTH (N/mm ²)	8	>10
STANDARD	EN 196-1	

*Results obtained at fluid consistency under lab conditions at 25°C ± 2: 17% water or 4.25 lit. per 25 kg bag. The mechanical characteristics will be higher if the weber.tec 305 HF is mixed at plastic consistency (less mixing water dosage)

*Properties listed above are only based on controlled laboratory samples and tests: Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

INSTRUCTIONS FOR USE

MORTAR PREPARATION

The slurry or mortar is obtained by mixing Rec Grout 747 with water. The amount of water used varies according to the workability required.

Add the powder to the water and mix for 3 minutes. To ensure a homogeneous and uniform mix, an electric mixer must be used. Do not mix with other hydraulic binders. The use of additives is absolutely prohibited.

Ideal application temperature is between +5°C and +35°C. If the application temperature is higher than 35°C, make sure to use cool water to keep the mixed grout temperature below 30°C.

Mixing			
	webertec 305 HF	WATER (lit)	VOLUME IN PLACE
PLASTIC CONSISTENCY	25kg	3.5 to 3.75 lit.	12.5 lit
FLUID CONSISTENCY	25kg	4.25 to 4.5 lit.	13 lit.

GROUTING

Build a solid leak-proof formwork. Saturate the concrete substrate with water for at least few hours prior to pouring. Remove all residual water. Pour Rec Grout 747 continuously, in one direction to avoid air pockets. The choice of installation method depends on the grouting thickness and the length of the gap. The grout can be applied up to a 5 cm thickness. Gaps with thickness up to 10 cm can be filled in several layers, depending on geometry and level of steel reinforcement. Once the grout starts to set, it should be cured either by a curing compound or if the configuration and the tightness of the forms allow by pouring 1 to 2 cm of cool water over the surface and maintaining it until the striking of the forms.

CURING

Protect the work against rapid drying from wind, sun and excessive heat by using a curing compound like Rec Cure E-4 or by covering with properly sealed plastic sheeting.

YIELD

12.5 to 14 litre per 25kg bag depending on consistency.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.