

REC PLAST SP125

HIGH PERFORMANCE WATER REDUCING ADMIXTURE FOR HSC

DESCRIPTION

REC PLAST SP125 is high performance superplasticising admixture formulated from selected polymers specially designed to enable the water content of the concrete to perform more effectively. This effect can be used in high strength concrete mixes to improve workability, to increase ultimate strengths or to facilitate a reduction in the cement content while sustaining and improving mix properties.

PRIMARY APPLICATIONS

- To produce high quality concrete of improved durability and water tightness.
- Recommended for high strength concrete mixes.
- Improved cohesion allows for use in mass concrete pours and piling.

FEATURES/BENEFITS

- Improved workability reduces placing and compaction problems.
- Allowing for high strength concrete production without excessive cement contents.
- Cement saving without affecting strength.
- Minimizing segregation and bleeding problems by improving cohesion.
- More durable concrete as a result of reduction in permeability and lower water to cement ratio.

COMPATIBILITY

REC PLAST SP125 can be used with all types of Portland cement and cement replacement materials. **REC PLAST SP125** is compatible with other Reckon admixtures used in the same concrete mix. If more than one type of admixture is to be used in the concrete mix, they must be dispensed to the concrete separately.

STANDARDS

REC PLAST SP125 complies with BS EN 934-2, Table 11.1 & 11.2 and ASTM C494 Type G.

TECHNICAL INFORMATION

Colour:	Brown liquid
Freezing point:	≈ -1°C
Specific gravity:	1.15 ± 0.03
Chloride content:	Nil
Air entrainment:	Typically less than 2% additional air is entrained above control mix at normal dosages

DIRECTIONS FOR USE

REC PLAST SP125 should be added to the concrete with the mixing water to achieve optimum performance.

An automatic dispenser should be used to dispense the correct quantity of **REC PLAST SP125** to the concrete mix.

DOSAGE

The guidance dosage of **REC PLAST SP125** is 1.00 to 2.50 litre per 100 kg of cementitious materials in the mix, including GGBFS, PFA or microsilica.

Representative trials should be conducted to determine the optimum dosage of **REC PLAST SP125** to meet the performance requirements by using the materials and conditions in actual use.

EFFECTS OF OVER DOSAGE

Overdosing of **REC PLAST SP125** will cause the following:

- Significant increase in retardation.

- Increase in workability.

Ultimate concrete strength will not be adversely affected and will generally be increased provided that proper concrete curing is maintained.

SETTING TIME

Although the setting time is dependent on the dosage of **REC PLAST SP125**, the following factors should be considered:

- Retardation is increased with lower levels of tri- calcium in the cement.
- Lower temperatures will delay the setting time.
- SRC cement gives higher retardation level than ordinary cement.
- Retardation level is increased when cement replacement materials are used in the concrete mix.

CLEANING

- **REC PLAST SP125** can be washed with fresh cold water.

PACKING

REC PLAST SP125 is available in 25 kg pails, 210 kg drums and 1000 kg bulks supply.

STORAGE

REC PLAST SP125 has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, Reckon Technical Department should be contacted for advice.

HEALTH & SAFETY

REC PLAST SP125 is not classified as hazardous material. **REC PLAST SP125** should not come into contact with skin and eyes.

In case of contact with eyes wash immediately with plenty of water and seek medical advice promptly.

For further information refer to the Material Safety Data Sheet.

WARRANTY: The Reckon Chemicals (Pvt) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED

Plot # 6, Akram Chock, Nadar Industrial Estate,

22 KM Ferozpur Road, Lahore.

Tell: +92-42-35454748-49

Web: www.reckonchemicals.com

Email: Info@reckonchemicals.com

