

# REC NEPHTHAPLAST 113

## HIGH-RANGE WATER REDUCING / RETARDING / SUPERPLASTICIZING ADMIXTURE

### PRODUCT

Rec Nephthaplast 113 is formulated from synthetic polymers and designed as a multi-purpose superplasticizer. This special formulation enables Rec Nephthaplast 113 to retain concrete workability for a longer time at low w/c at during hot weather concreting. It can maintain good mixture appearance without segregation or bleeding. At intentionally higher dosages, Rec Nephthaplast 113 has the effect of a set retarder.

### PROPERTIES

- Water reducing
- Superior slump retention. Ease of delivery to point of placement
- High workability-ease of placing and compaction without segregation
- Ease of pumping. No bleeding
- Enhances workability
- Improves workability recommended for congested reinforced structures
- Compatible with concrete containing pozzolanic materials

### SCOPE OF USE

Rec Nephthaplast 113 to ensure that plastic concrete remains workable for more than 1 hour at high temperatures. Ideal for construction of dams, locks, road works, architectural concrete, light or heavy prefabrication, ready-mix concrete, and pumped concrete.

### CHARACTERISTICS

Appearance	Liquid
Color	Brown
Specific gravity	1.18 ± 0.03
Chloride content	Zero to BS 5075
Air entrainment	Up to 1.5% depending on dosage rate and concrete proportioning

### APPLICABLE STANDARDS

Rec Nephthaplast 113 complies with:  
ASTM C 494 – Type D & G.  
BS 5075 Part 1, BS EN 934, Part 2

### INSTRUCTION FOR USE

Rec Nephthaplast 113 is totally miscible in water. It is to be added to the concrete mixture during the mixing cycle at the same time as the mixing water. No extension to normal mixing time is necessary.

### DOSAGE

Trials should be conducted to determine the optimum dosage of Rec Nephthaplast 113 for a particular mixture. A dosage of 600 to 1300 ml per 100 kg of cementitious materials is recommended.

The required dosage for a specific job conditions to ensure controlled delay in setting and secure the desired workability should be determined by in-situ trials.

### EFFECTS OF OVER DOSING

A severe over dose of Rec Nephthaplast 113 will result in the following:

- Delay in setting
- Increase in air content
- Higher workability

### COMPATIBILITY

Rec Nephthaplast 113 can be used in all types of Portland cements, sulfate-resisting cement, and concrete with cementitious materials.

Rec Nephthaplast 113 should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing Rec Nephthaplast 113, they must be dispensed separately. Consult the company's technical dept. for advice.

### SPECIFICATION CLAUSE

Rec Nephthaplast 113 is high-range water reducing and retarding plasticizing concrete admixture manufactured to the following specification:

Rec Nephthaplast 113 can be used in all concrete as mentioned at dosage between 200 to 1300 ml per 100 kg of cementitious materials in accordance with the manufacturer's instructions.

Specific Gravity 1.18 ± 0.03

Complying with ASTM C 494 Types D & G.

Composition: High molecular weight refined synthetic polymers derivatives and other refined chemicals.

### DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment. Such equipment can be supplied by the company.



# REC NEPHTHAPLAST 113

## PACKAGING

Rec Nephthaplast 113 is supplied in: Bulk, barrels.  
Storage tanks can be provided for bulk use.

## STORAGE

Rec Nephthaplast 113 can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

## HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

## QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.