

# REC NEPHTHAPLAST 72

## High-range water reducing/retarding/superplasticizer admixture

### PRODUCT

Rec Nephthaplast 72 is a sustainable multi-component admixture which is carefully formulated to enhance the quality and performance characteristics of plastic and hardened concrete. Its unique chemistry results in more complete and efficient hydration of the cementitious materials in the concrete matrix, and provides improved strength, durability, finishability and overall appearance.

Rec Nephthaplast 72 enhances concrete by extending its range of economic and useful applications.

Dispersing the cement particles evenly and efficiently throughout the mix makes the cement hydration process more efficient, increasing the strength gain overall. As a result, with the use of admixtures, a lesser quantity of cement is required to achieve the same strength as for a mix without admixtures.

### PROPERTIES

- Provides increased slump and flowability without increased water content
- Improves concrete quality by reducing the water / cement ratio for a given degree of workability
- Improves workability and consolidation
- Provides lubrication and enhances pumpability
- Improves manufactured sand mixes
- Provides uniform, normal set, including GGBF (slag), silica fume and fly ash mixes.
- Improves concrete durability

### SCOPE OF USE

Rec Nephthaplast 72 is recommended for all areas of use of concrete in the ready-mix industry:

- Super slump retaining concrete with equal or less water content than conventional admixtures
- Concrete mixtures containing silica fume, GGBS, or PFA
- Concrete with high resistance against aggressive media
- Long distance transport
- Hot weather concreting
- Mass concrete
- Pumped concrete
- Ready-mix concrete
- Prestressed concrete
- Incubated concrete
- Paving and industrial floors
- Heavily reinforced concrete works
- Long hauling concrete deliveries

### CHARACTERISTICS

Appearance	Liquid (Dark Brown)
Specific gravity at 20°C	1.105 ± 0.02
Chloride Content	NIL – BS 5075/EN 934-2

### APPLICABLE STANDARDS

Rec Nephthaplast 72 complies with:  
ASTM C – 494 – Type G

### INSTRUCTIONS FOR USE

Rec Nephthaplast 72 should be dispensed after all concrete constituents are charged in the central mixer, preferably after approximately 70% of mixing water addition.

### DOSAGE RATES

Range of dosage rates: from 600 to 2500 ml per 100 kg of cementitious content.

Dosage above the recommended values can be employed. Still, the required dosage for a specific job with controlled delay in setting and workability should be determined by in-situ trials.

Admixture demand varies with w/b of the concrete, cement type, pozzolanic materials and ambient temperature.

Trials are to be conducted prior to use in order to determine required performance, including workability retention, setting, and strength development.

### EFFECTS OF OVER DOSING

Overdose of Rec Nephthaplast 72 may result in the following:

- Delay of initial setting
- Higher workability
- Impair consistency & cohesion
- Higher Ultimate strength when curing practices are implemented as per ACI 308R

### COMPATIBILITY

Rec Nephthaplast 72 is compatible with all types of Portland cement, class C and F fly ash, silica fume, ground granulated blast furnace slag, fibers and approved air entraining, accelerating, retarding, and high-range water-reducing admixtures. For best results, each admixture must be dispensed separately into the concrete mix.

Rec Nephthaplast 72 is compatible with naphthalene sulfonate and melamine sulfonate-based superplasticizers. Consult Reckon Chemical's technical dept. for advice.



## PACKAGING

Rec Nephthaplast 72 is supplied in:  
1000 liter containers.

## STORAGE

Rec Nephthaplast 72 can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

## HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation.  
In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention.  
If swallowed, do not induce vomiting and seek medical attention.

## QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.