

RECTOP 1001

PREMIUM POLYMER & MICROSILICA MODIFIED REPAIR & OVERLAY MORTAR

DESCRIPTION

RECTOP 1001 is a latex and micro silica modified cementitious mortar designed for use as a floor or deck topping at thicknesses of 1/16" to 3/8" (1.6 mm to 10 mm). This product is a single-component formula which incorporates a powder latex technology. It provides excellent durability under freeze-thaw cycling as well as reducing the ingress of water and de-icing salts. RECTOP 1001 offers normal set times in a trowelable consistency for easy workability.

PRIMARY APPLICATIONS

- Parking decks
- Pavements
- Joints
- Marine structures
- Curbs and gutters
- Ramps
- Floors
- Walkways

FEATURES/BENEFITS

- Provides a strong, wear resistant thin overlay
- Excellent durability in freeze-thaw cycles
- Contains an integral corrosion inhibitor
- Excellent bond to prepared concrete
- Reduces the penetration of water and de-icing salts for substrate protection
- Suitable for both interior and exterior use Can contribute to LEED points

TECHNICAL INFORMATION

Typical Engineering

Data under laboratory conditions @ 73oF (23oC) 50% RH

Compressive Strength ASTM C 109, 2" (50 mm) cubes

@ 2.9 qts (2.7 L)/50 lb (22.7 kg) bag.

Age -----Strength

1 day. 2,800 psi (19.3 MPa)
7 days. 5,000 psi (34.5 MPa)
28 days. 6,700 psi (46.2 MPa)
56 days. 7,900 psi (54.5 MPa)

Linear Shrinkage

ASTM C 157
3 days. 0.02%
7 days. 0.05%
14 days. 0.08%
28 days. 0.10%
56 days. 0.11%

Unit Weight. approx. 130 lb/ft³ (2082 kg/m³)

Flexural----- Strength

ASTM C 348

7 days.....950 psi (6.6 MPa)
28 days..... 1,150 psi (7.9 MPa)
Split Tensile Strength ASTM C 496
7 days. 500 psi (3.5 MPa)
28 days.....550 psi (3.8 MPa)

Freeze/Thaw Resistance

ASTM C 666
Procedure A
300 cycles.100% relative dynamic modulus

Working Time..... 30 to 40 minutes

Initial Set. 1 to 1.5 hours

Final Set. approx. 3 hours

Appearance: THIN-TOP SUPREME is a free-flowing powder as packaged. After mixing and placing, the color may initially appear darker than the surrounding concrete. The color will lighten up substantially as it cures and dries out, though it may always appear somewhat darker than the surrounding concrete.

PACKAGING

RECTOP 1001 is packaged in 50 lb (22.7 kg) moisture resistant bags. **Yield:** 0.43 ft³/bag (0.012 m³) when mixed with 3 qt (2.8 L) of water. Typical water requirement is 2.75 to 3.5 qt (2.6 to 3.3 L)/bag.

SHELF LIFE

1 years in original, unopened package

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Properly clean profiled area.

Priming: Clean and prime exposed steel with RECDUR 111.. Concrete should be primed with a spray or brush coat of RECDUR 111.. The primer coat of RECDUR 111. must be allowed to thoroughly dry prior to the application of the repair mortar. Alternately, a Saturated Surface Dry (SSD) concrete surface can be primed with a scrub coat of THIN TOP SUPREME. The repair must be made before the scrub coat dries out.

Mixing: Single bags may be mixed with a drill and “jiffy” mixer. Use a paddle type mortar mixer for large jobs. All material should be in the proper temperature range of (15°C) to (30°C). Add the appropriate amount of water 2.75 to 3.5 qt (2.6 to 3.3 L) per bag for the batch size and then add the dry product. Mix for 3 to 5 minutes.

Placement: Discharge material from mixer immediately and place on to the repair area. For repairs, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. Work material into place by floating or troweling. On large areas, use screed strips with a vibratory screeding to level.

Finishing: This product is designed for finishing with a float or broom appearance. Do not add additional water to the surface during the finishing operation; use Reckon evaporation retarder. For a hard, flat troweled surface, delay finishing until the product is near final set (approx. 3 hours) to reduce the risk of blistering during troweling.

Curing and Sealing: Proper curing procedures are important to ensure the durability and quality of the repair. To prevent surface cracking, cure the material with a high solid curing compound, such as **REC CURE E-1 C-309**.

Note: Do not use a solvent based curing compound on this product. If a curing compound is not desired, cover with polyethylene for a minimum of 3 days. Do not wet cure. Always re-establish floor and slab joints when using this product as an overlay.

PRECAUTIONS/LIMITATIONS

- Do not wet cure. Do not use a solvent-based curing compound on this product.
- Do not allow repairs to freeze until the material has reached a minimum of 1,000 psi (7 MPa) compressive strength.
- Use only potable water for mixing.
- Do not add admixtures or sand.
- Do not use material at temperatures below 45°F (7°C) or above 100°F (38°C).

- No heavy traffic until the product has cured.
- Mixing partial bags may yield variable results; always mix full units.
- Store product in a dry place.
- For repairs and toppings thicker than 3/8" (9.5 mm), use RECTOP 1001.
- In all cases, consult the Safety Data Sheet before use.

CLEAN-UP

Clean tools and equipment with water before the material hardens. Hardened THIN-TOP SUPREME will require removal by mechanical means.

WARRANTY: The Reckon Chemicals (Pvt.) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
21 CCA, BLOCK B, KHAYABAN-E-AMIN, LAHORE
Tell: +92-42-35452620, +92-42-35230419
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

