

RECTOP FRC

FIBER-REINFORCED CONCRETE RESURFACER

DESCRIPTION

RECTOP FRC is a polymer modified, fiber-reinforced concrete resurfacing mortar. Adding only water, RECTOP FRC provides a fresh, aesthetically pleasing appearance to new concrete that has been marred by rain or plastic covering, old or spalled concrete, and salt damaged concrete.

PRIMARY APPLICATIONS

- Driveways
- Sidewalks
- Pool decks
- Garage floors
- Elevated slabs
- Vertical concrete surfaces

FEATURES/BENEFITS

- Excellent working time at 70°F (21°C)
- Polymer modified
- Micro-fiber reinforced
- Suitable for freeze-thaw environments
- Open to foot traffic in 4 hours, rubber tire traffic in 12 hours at 75°F (24°C)

PACKAGING

RECTOP FRC is packaged in 40 lb (18 kg) moisture resistant bags. The yield of RECTOP FRC is 0.48 ft³ (0.01 m³) per bag. A mixed unit of RECTOP FRC will cover approximately 92 ft² (8.6 m²) at 1/16" (1.6 mm).

SHELF LIFE

2 years in original, unopened package

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and be free of curing and sealing compounds, dust, dirt, paint, efflorescence, oil and all other contaminants. Typically, pressure washing the surface with a commercial pressure washer (3000 psi, 4 GPM) (21MPa, 0.25 L/s) and allowing to fully dry will be sufficient for preparation. In areas of heavy contamination, preparing the concrete through mechanical means is recommended.

Priming: Apply RECTOP FRC to dry surfaces. Although a primer is typically not needed, if the concrete is very porous RECTOP FRC bonding adhesive must be used to prevent pinholes from forming in the RECTOP FRC. Please refer to the RECTOP FRC technical data sheet for further instructions.

Mixing: All materials should be conditioned to the appropriate temperature range of 50°F - 90°F (10°C - 32°C) prior to mixing and placement. RECTOP FRC mixes with 4.5 quarts (4.3 L) of clean, potable water for standard overlay applications. Up to an additional pint (0.4 L) can be added when the temperature exceeds 80°F (27°C). For repairing deeper spalls prior to overlaying, RECTOP FRC can be mixed with 3.5 to 4 quarts (3.3-3.8 L) of water to make a stiff paste suitable for spall repairs. Place 80% of the mixing water into a clean pail. Slowly add the dry RECTOP FRC powder into the mixing pail. During this time, the material should be mixed with a drill and "jiffy" type mixing paddle. Slowly add the remaining 20% of the mixing water to the pail and mix for 3 minutes to achieve the desired consistency. Place immediately.

Coloring: RECTOP FRC can be integrally colored. Add the desired liquid or dry colorant to the mixing water and stir until colorant evenly disperses throughout the water. Continue mixing in the RECTOP FRC as directed. The Reckon Chemical Company does not warrant any colored application. For even results, it is a best practice to "box" all mixing water that has been colored prior to mixing individual bags of RECTOP FRC. Colored results vary based on the colorant and amount used.

Placement: Place the mixed RECTOP FRC onto the concrete in the desired area. For best adhesion to the concrete, use a scrub brush or stiff street broom to scrub the material onto the prepared

substrate. Following the initial placement of the material to the concrete, finish as desired, using either a trowel or a broom. The maximum placement depth of RECTOP FRC is 3/8" (9.5 mm). If multiple lifts are to be applied, score the previous lift after placing; this will provide a great surface to mechanical bond subsequent lifts over. Since RECTOP FRC is a thinly applied material, surface and air temperatures greatly affect the working time of the material. On hotter days, it is best practice to work in small, controlled areas to avoid cold joints. Use Reckon Chemical's evaporation retardant to retain moisture in the material and to provide longer finishing time. Working from joint to joint in the base concrete is a good practice. All saw cuts and joints in the base concrete will have to be honored through the RECTOP FRC material.

Curing and Sealing: Proper curing procedures are important to ensure the durability and quality of the repair. As soon as the material can be walked on without harming the finish, apply a water-based cure and seal compound to the RECTOP FRC. If you can apply a cure and seal sooner from the sides of the project, then do so. The use of Reckon Chemical's CLEANERS is highly recommended for use on this product.

PRECAUTIONS/LIMITATIONS

- Avoid applying material in direct sun
- Mixing partial bags will give variable results; always mix full units.
- Use only potable water for mixing.
- DO NOT use this material below 50°F (10°C).
- DO NOT use a solvent-based cure and seal on this product.
- DO NOT use plastic or other covering means to cure REC RE-COVER, for discoloration will occur.
- Store product in a cool, dry place.
- In all cases, consult the Safety Data Sheet before use

CLEAN-UP

Clean all tools and equipment with water prior to the material hardening. REC RE-COVER develops a tenacious bond and is difficult to remove after drying.

WARRANTY: The Reckon Chemicals (Pvt.) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
21 CCA, BLOCK B, KHAYABAN-E-AMIN, LAHORE
Toll: +92-42-35452620, +92-42-35230419
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

