

REC GROUT 730

GENERAL PURPOSE NON-SHRINK GROUT

DESCRIPTION

REC GROUT 730 is a ready-to-use, cementitious grout formulated from selected aggregates, special cement, and additives. It is designed for applications where non-shrink properties are required. **REC GROUT 730** is specially formulated to produce a shrinkage-compensating grout suitable for a wide range of applications.

PRIMARY APPLICATIONS

- Filling of shutter tie-rod holes and openings.
- Repair of damaged concrete areas.
- Concrete jacketing for slabs, columns, beams, and footings.
- Fixing and joining concrete elements.
- Closing or filling concrete and precast elements.

FEATURES/BENEFITS

- Non-shrinking.
- Easy to apply.
- Excellent resistance to shock and vibration.
- Suitable for pumping applications.

TECHNICAL INFORMATION

Grey powder	Appearance
Free from chlorides and metallic particles	Chloride and metallic particles
12	pH
Fresh density	2.3 kg/dm ³
Compressive strength	40 MPa at 28 days
Application Temperature	+5°C to +35°C

APPLICABLE STANDARD

ASTM C1107

DIRECTIONS FOR USE

SUBSTRATE PREPARATION

REC GROUT 730 may be applied on sound concrete, masonry, rock, or similar substrates. Remove damaged concrete and laitance by chipping with a pick or cold chisel to obtain a rough and sound surface. The surface must be free from all traces of grease, oil, dust, and other contaminants. Saturate the surface thoroughly with water by copious spraying immediately before application and, where possible, approximately 6 hours before application. Remove any standing or excess water before placing the grout.

PRODUCT PREPARATION

REC GROUT 730 is prepared by mixing the powder with approximately 6–7 liters of clean water. Add the powder gradually to the required quantity of water and mix for approximately 3 minutes. An electric mixer should be used

to obtain a homogeneous and uniform mixture. Do not mix with other hydraulic binders. The use of additional additives is not permitted.

PRODUCT APPLICATION

Prepare a solid, leak-proof formwork before placing the grout. Pour **REC GROUT 730** continuously, either by gravity or by pressure-pump placement, and place the grout in one direction to minimize the possibility of air pockets. The applied thickness may be up to 10 cm. Continuous grout flow is essential. Sufficient quantities of grout and water should be available for uninterrupted mixing and placement to prevent discontinuity in the grout flow.

CURING

Protect the applied grout against rapid drying caused by wind, direct sunlight, and excessive heat. Curing may be carried out using a suitable curing compound, such as **REC CURE E-4**, or by covering the applied grout with properly secured plastic sheeting.

PACKAGING

REC GROUT 730 is supplied in various packaging sizes and quantity of the product varies with the demand of clients.

STORAGE

Shelf life is 12 months from the date of manufacture when stored in the original, unopened packaging, under cover, in dry conditions, away from humidity, and protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

While using the product, gloves, a mask, and safety goggles should be worn. Splashes on the skin or in the eyes should be washed immediately with clean water. In case of prolonged irritation, seek medical advice.

QUALITY STATEMENT

All our products are manufactured to comply with our internal quality management system to ensure consistency and quality.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use. This Data Sheet version is the latest one. The company may modify it without any prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's head office located in Lahore.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd, Lahore. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

WARRANTY: The Reckon Chemicals (Pvt.) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
21 CCA, BLOCK B, KHAYABAN-E-AMIN, LAHORE
Tell: +92-42-35452620, +92-42-35230419
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

