

REC GROUT 735

Non shrink very high strength grout

PRODUCT

Rec Grout 735 is a blend of portland cement, special admixtures and proprietary aggregates designed to provide high flexural and compressive strength performance from plastic to fluid consistencies. **Rec Grout 735** is non-metallic, non-shrink, non-gas forming and contains no chlorides or aluminum powders. It is specially used when repair of high strength concrete is required.

SCOPE OF USE

- Assembly of pre-cast parts made of reinforced or pre-stressed concrete
- Bridge bearing applications
- Concrete jacketing for slabs, columns, beams and footings
- Reblocking / restumping / void filling applications
- Closing or filling around pipes in water tanks / swimming pools
- Pumpability properties
- Anchoring of steel bars
- Jointing
- Fixing industrial equipment and heavy machinery, mounting plates
- Vertical shoring
- Void filling operations
- Excellent shock & vibration resistance

ADVANTAGES

- Non-shrinking
- High strength
- Easy to apply
- Resistant to sea water and sulfates
- Liquid or plastic consistency

*COMPRESSIVE STRENGTH

AGE	1 day	7 days	28 days
COMPRESSIVE STRENGTH (N/mm ²) – BS EN 12190 at 22°C ± 1	32	57	72
STANDARD	BS-EN 196-17	BS-EN 196-1	BS EN 196-1*

*FLEXURAL STRENGTH & TENSILE STRENGTH at 28 days

AGE	28 days
FLEXURAL STRENGTH (N/mm ²) – BS EN 196 - 1	above 7
TENSILE STRENGTH (N/mm ²) – BS 6319:PART 7: 198528	3.8

*Results obtained at fluid consistency: 12.5% water or 6.25 lit. per 50 kg bag.

The mechanical characteristics will be higher if the **Rec Grout 735** is mixed at plastic consistency: 11% water or 5.5 the compressive strength can exceed 80 MPa at 28 days.

CHARACTERISTICS

Appearance	Grey powder
Grain size	0 to 4.75 mm
Free from chlorides and metallic particles	
Fresh density (BS 1881:83)	2340 kg/m ³
Lengthchange	below 0.05% @ 28 days (ASTM C157-03)
Pull off stress	> 1.5 N/mm ² @ 28 days (BS 1881 Part 207)

APPLICABLE STANDARDS

BS EN 196 Part 1
BS 1881 Part 207
ASTM C 157-03
BS 6319 – Part 7- 1985
BS 1881: 83
ASTM C 1107



REC GROUT 735

INSTRUCTIONS FOR USE

PRODUCT PREPARATION

Grout or mortar is obtained by mixing **Rec Grout 735** with clean water. The amount of water used depends on the workability required. Add the powder to the water and mix for 3 minutes. To ensure a homogeneous and uniform mix, an electric mixer must be used.

Mixing

	webertec 301 HCS	WATER (l)	VOLUME IN PLACE
Mortar	50 kg	5.5 lit.	26 lit
Grout	50 kg	6.255 to 6.75 lit.	28 lit.

(l): Half quantity of water is required for 25 Kg package

PRODUCT APPLICATION

For grouting /jacketing/repair

Rec Grout 735 can be used for thickness up to 10 cm. Existent surface needs to be roughened and cleaned. Ensure damping the surface with water before the application. Thickness above 10 cm can be practiced up to 30 cm in case of epoxy anchoring dowels (rebars) installation in the existent structure by (pouring) the Pure epoxy into drilled holes in the existent structure, then steel mesh to be connected to Dowels (rebars). Ideal Application temperature is between +5°C and 35°C

For Shoring/Soil Nailing Applications

Rec Grout 735 can be used for grouting the inclined holes in shoring applications. Hole diameter must not exceed 20 cm, depth of hole will be determined by structure engineer. **Rec Grout 735** is high fluid and non-shrink properties ensure excellent anchoring/friction with soil/rocks. If the application temperature is higher than 35 °C, make sure to use cool water to keep the mixed grout temperature below 30°C.

CURING

Protect the work against rapid drying from wind, sun and excessive heat by using a curing compound like **Rec Cure E-4** or by covering with properly secured plastic sheeting.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

PRECAUTIONS

Substrate must be sound and resistant. It should be saturated with water a few hours prior to installation. Remove all water used in wetting support prior to installation of **Rec Grout 735**. Do not mix with other hydraulic binders.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.