

REC NAPHTHAPLAST N95

Super Plasticizer - High Range Water Reducing Admixture

DESCRIPTION

REC NAPHTHAPLAST N95 is a liquid admixture based on naphthalene polymer associated with chemical synthesis products. **REC NAPHTHAPLAST N95** produces concrete of high workability concrete requiring little or no vibration during placement. **REC NAPHTHAPLAST N95** provides up to 25% reduction in free water without loss of workability, resulting in high-quality concrete of reduced permeability and increased early strength gain.

PROPERTIES

REC NAPHTHAPLAST N95 provides the following benefits:

- As a superplasticizer for facilitating concrete placement.
- As a normal water-reducing admixture to enhance mechanical properties at all ages.
- Cement content optimized for desired mechanical strength.
- No segregation.
- High strength hardening accelerator.

SCOPE OF USE

REC NAPHTHAPLAST N95 is recommended for all cement types in the following areas:

- Heavily reinforced concrete works.
- Paving and industrial floor.
- Ready-mix concrete.
- Precast concrete elements.
- Concrete placement at low temperatures.
- All concrete requiring fluid consistency.
- Concrete with low water/cement.

Technical Information

Appearance	Liquid
Color	Brown
Specific gravity at 25°C	1.165 ± 0.015
Chloride content	Nil (BS 5075)
Air Entrainment	Up to 2.0% depending on dosage rate and concrete proportioning.

APPLICABLE STANDARDS:

REC Naphthaplast N95 complies with ASTM C 494 Type G, BS 5075.

INSTRUCTIONS FOR USE

REC Naphthaplast N95 is totally miscible in water. No extension to the batching time is necessary. Do not add to dry cement. **REC Naphthaplast N95** can be used on site to produce fluid concrete to a required workability. Make sure that the concrete is agitated for not less than 2 minutes at 15-20 rpm before casting.

DOSAGE

Trials should be conducted to determine the optimum dosage of **REC Naphthaplast N95** for a particular mixture. A dosage of 0.5-2.6% per 100 kg of cementitious material is recommended. Further the required dosage for a specific job with controlled delay in setting and workability should be determined by in-situ trials.

EFFECT OF OVER DOSE

Severe over dose of **REC Naphthaplast N95** will result in the following:

- Delay in setting.
- Increase in air content
- Higher workability

COMPATIBILITY

REC Naphthaplast N95 can be used in all types of Portland cement, sulfate resisting cement and cementitious materials. **REC Naphthaplast N95** should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing **REC Naphthaplast N95**, they must be dispensed separately. Please consult the company's Technical Department for advice.

DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment.

PACKAGING

REC Naphthaplast N95 can be supplied in drums and tanks.

STORAGE

Up to 2 years when stored in accordance with manufacturer's instructions.

HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use. This Data Sheet version is the latest one. The company may modify it without any prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's head office located in Lahore.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd, Lahore. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

WARRANTY: The Reckon Chemicals (Pvt) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
Plot # 6 Km off Manga Road, Glamour Stop,
Opp. Sundar Industrial Estate, Lahore.
Tell: +92-42-35395224-225
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

