

REC FIBER PP 174

Fibrillated polypropylene fibers additive for concrete and plaster

DESCRIPTION

Rec Plast PP-174 is a high-performance micro propylene fiber designed and formulated specially for the use in mortar and concrete. It is used to inhibit the occurrence of small cracks which can occur through plastic shrinkage, premature drying, and early thermal volume changes of the hardened cementitious materials. Due to their specific characteristics and ease of dispersion in concrete, they can be mixed at any stage in the concrete regardless of the consistency of concrete. They are extremely resistant to alkali. The hydration of the cement as well as mixing water requirement of concrete and mortar are not affected by the use of Rec Plast PP-174 fibers.

SCOPE OF USE

- Canal Lining Works
- Industrial / Commercial Floorings
- Tunnel Lining Works
- Concrete Roads / Pavements
- Water Storage Tanks
- Swimming Pools
- Rooftops
- Pre-stressed concrete electricity poles
- Rock / Slope Stabilization
- Internal & External Plaster
- Precast Products – Pipes
- Structural Repairs & Restoration
- Concrete Slabs
- Shotcreting
- Mine Lining Works
- Roofing Sheets
- Bridges – Wearing Coat
- Stamped Concrete
- Decorative concrete
- Slab-on-Grade
- Tilt-up Panels

ADVANTAGES

Since they are completely integrated in the structure of the concrete and mortar, they constitute a secondary reinforcement which improves the general material characteristics:

- Inhibits plastic shrinkage cracks & settlement cracks
- Does not allow moisture or water to seep in due to reduction in permeability
- Fibrillated (Mesh) structure ensures better binding & anchoring with concrete aggregates.
- Distributes localized stresses & increase fatigue resistance

- Reduces unequal bleeding so solids in concrete do not settle unevenly & enhances cement hydration in fresh concrete there by increasing tensile & flexural strength
- Improves fire resistance characteristics in concrete there-by reducing risk of spalling
- Provides impact and abrasion resistance

TECHNICAL INFORMATION

Composition	100% Virgin Polypropylene
Type	Fibrillated Form
Length	6, 12, 15, 20, 30, 40, 50,60, & 120
Specific gravity	0.91 gr/cm³
Modulus of elasticity	500 ksi
Melt point	165°C
Ignition point	>360°C Alkali, acid and salt resistance High

BENEFITS

- Reduction in seepage / dampness
- Reduced honeycombing & bleeding problems, ensuring uniform hydration
- Better quality & faster completion of work
- Reduce shrinkage cracks by over 90%
- Protects primary steel reinforcement from corrosion
- Ensuring better hydration

SHELF LIFE

Should be stored in dry conditions up to 12 months.

DIRECTION OF USE

Rec Plast PP-174 could be introduced in dry or wet mixing. Since they have the advantage of mixing in concrete or mortar in all phases; they could be even introduced in truck mixers, in which case 5 min. of mixing at high speed would be required or 70 revolutions after the addition of Rec Fiber PP 174 100 to ensure uniform distribution.

SPECIFICATION

Rec Plast PP-174 shall be used in strict accordance with the supplier' s recommendations and within time as specified in ASTM C94.

Rec Plast PP-174 complies with ASTM Designation C1116 Type III 4.1.3 and with applicable building codes. Standard ACI 302 procedures for placing, finishing and curing shall be followed when using Rec Plast PP-174.

DOSAGE RATES

0.60 to 0.9 kg/m³.

Higher addition dosages may be used to produce special concrete properties as per requirements.

Excessive overdosing will generally produce a reduction in workability, and an increase in the cohesiveness of the mixture.

PACKAGING

23kg paper bag

HEALTH & SAFETY

In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention. paste. Use surface adhesion

QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their applications are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that the Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

WARRANTY: The Reckon Chemicals (Pvt.) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
21 CCA, BLOCK B, KHAYABAN-E-AMIN, LAHORE
Tel: +92-42-35452620, +92-42-35230419
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

