

REC EPO INJECTION 52

LOW VISCOSITY STRUCTURAL CONCRETE CRACK EPOXY INJECTION

DESCRIPTION

REC EPO INJECTION 52 is a low viscosity, high modulus structural epoxy adhesive used for a variety of repair projects. With its low viscosity, it is perfect for horizontal gravity- feed repair of fine to medium size cracks and can be used in temperatures between 10°C and 35°C. Its bonding and sealing capabilities for interior and exterior slabs are exceptional. It can also be used as an epoxy mortar for spall repair when mixed with aggregate.

KEY FEATURES

- 100% solids, solvent free system with low VOC content.
- Pressure injection and gravity feed structural crack repair in horizontal concrete, masonry for cracks from 3mm to 6mm.
- Epoxy resin binder for epoxy mortar patching and overlay of interior surface using addition of aggregate.
- Shear fracture repairs on interior and exterior concrete slabs good chemical resistance to a wide range of mild alkalis, diluted acids and solvents.

TECHNICAL INFORMATION

Color	Amber tint
Mixed Viscosity	500 cps
Gel Time (+24°C)	20 minutes
Mixing Ratio	2:1 & 1:1
Compressive Strength 7 days	70 MPa
Shear Bond Strength 2 days	8 MPa
Shear Bond Strength 7 days	11 MPa
Elongation at break 7 days	1.8%
Water Absorption 24 hours	0.28%

DIRECTIONS FOR USE

a. INSTRUCTIONS

Always be sure the bonding surfaces are prepared in advance before starting a new cartridge or mixing Product. If possible, schedule dispensing to consume an entire cartridge at one time with no interruption of the flow.

b. SURFACE PREPARATION

Old concrete must be clean, profiled or textured. New concrete must be a minimum of 28 days old. Before using **REC EPO INJECTION 52**, make sure that the surfaces to be bonded are sound and clean so there is no dust, dirt, grease, wax, oil, or any other contaminant present. Smooth surfaces should be mechanically roughened with a wire brush or sand paper before application.

c. CARTRIDGE SET-UP

While preparing cartridge, keep in an upright position to prevent material from leaking from cartridge.

- Shake cartridge for 1 minute then stand cartridge upright for 1 minute allowing bubbles to rise to the top.
- Place cartridge into the dispenser, and hold the dispenser pointing upward at about 45° angle due to the product's low viscosity. Remove plastic cap and plug.
- Dispense enough material into a disposable container until both resin and hardener flow evenly.

- Insert the flow control port and then the nozzle to the top of the cartridge. Still holding the dispenser at about a 45° angle, slowly dispense the material up through the nozzle and dispose of 1-2 trigger pulls.

d. BONDING AGENT APPLICATIONS

For bonding fresh concrete to hardened concrete or when repairing concrete spalls use as a bonding agent: Use a brush or roller and apply an even coat of the mixed **REC EPO INJECTION 52** to the clean and prepared concrete surface. While the epoxy is still tacky, place fresh concrete over the top of the mixed epoxy.

For bonding hardened concrete to hardened concrete: Use a brush or roller and apply an even coat of the mixed **REC EPO INJECTION 52** to the clean and prepared concrete surface. Make sure to fill all gaps between the two concrete surfaces.

e. GRAVITY FEED CRACK REPAIR FOR HORIZONTAL APPLICATIONS

REC EPO INJECTION 52 is formulated to repair hairline, fine to medium sized and large size cracks. For best results, cut a groove to open up the crack using an abrasive or diamond blade to a width 6mm and minimum depth 10mm. Use a wire brush to abrade and then blow out the crack to remove all dust, dirt, grease, wax, oil or any other contaminants. Pour or inject **REC EPO INJECTION 52** into the crack and its self-leveling ability will fill the entire area. Repeat application if necessary to completely fill the crack. Follow the cartridge preparation instructions.

f. SPALL REPAIR

To avoid a feathered edge, cut around the spall into sound concrete with a grinder or circular saw using a diamond or concrete abrasive blade. The edge cut should be equal to the maximum depth of the spall or to at least a minimum depth 20mm avoid a feathered edge.

Chip out all loose concrete within the entire spall to a minimum depth 20 mm. Follow surface preparation instructions to clean the spall. Estimate the amount of product needed and slowly add 4-5 parts by volume of Kiln dried sand or aggregate of choice and mix well, pour and trowel until smooth/ level. Maximum mortar thickness is 40mm per coat.

g. CRACK INJECTION SYSTEM FOR VERTICAL CRACKS

Before repairs are attempted, the crack should be analyzed to determine the type of repair that is required. Cracks in concrete and wood members are classified as either active (moving) or dormant. Dormant cracks may occur with one-time overload events such as earthquakes or floods. For dormant cracks in a structure that is to be rehabilitated, structural crack injection is recommended. By contrast, active cracks are caused by inadequate design, seasonal heaving, temperature swings or repeated overloading.

h. PREPARATION

Clean the surface immediately surrounding the crack with a wire brush to achieve a proper bond. Remove all dust, debris, oil and any other contaminants from the crack by blowing out with clean, oil- free compressed air. For best results crack must be dry at the time of injection. If water is seeping from crack, steps must be taken to stop the flow in order to achieve desired repair.

REC DUR 102 is ideal to be used as capping paste for the crack injection procedure. Place and secure injection ports with **REC DUR 102**, taking care not to leave any pin holes. Port spacing should be approximately 15 – 30cm apart (typically the width of the concrete member). Do not allow the epoxy to block the passage between the port and the crack face. Place additional **REC DUR 102** between the ports making sure the entire face of the crack is sealed off and ports are securely fastened to the concrete. If the crack is evident and accessible on the back side of the concrete member, seal with capping paste. See **REC DUR 102** for cartridge set-up.

i. INJECTION

- Attach the tube assembly to the barbed end of nozzle.
- Attach other end of tubing to the bottom injection port. Inject epoxy into port until there is flow from adjacent port or until epoxy stops flowing. Plug the port injecting into and attach tubing to adjacent port. Continue procedure until complete.
- Leave the tubing attached to the last port on each crack for 30 seconds under pressure to assure crack is completely filled.
- Allow Injection resin to cure (at least 24 hours). Ports and capping material can be removed with a chisel and/or grinder.

Note: Some cracks may take more time to inject. Cracks may be smaller in width (or larger) than they appear from the surface.

j. DISPENSING AND INJECTION TIPS

PNEUMATIC DISPENSER

Must be used with an air pressure regulator. Start at a low setting and gradually increase pressure as needed until desired epoxy flow. Use maximum 275 kPa (40 psi) air pressure. Excessive pressure may result in cartridge plunger leakage. For basement walls (where back side of concrete is not accessible) inject with slightly higher viscosity, **REC EPO INJECTION 52**. This is a unique thixotropic gel that will feed into small cracks and bridge the back side without run off. Do not dispense epoxy through gelled mixer nozzle. If epoxy gels in nozzle, replace nozzle before continuing.

k. CURING

REC EPO INJECTION 52 is fully cured in 24 hours. After such time, ports and capping material can be removed with a chisel and/or grinder.

l. APPLICATION TEMPERATURE

Substrate and ambient air temperature should be between 10°C and 35°C. When the work environment or substrate falls below 21°C, condition the product to 21°C – 24°C prior to use. Cold product will react (cure) slower and product that is too warm will react (cure) much faster than normal.

m. CLEAN UP

Clean tools and equipment with white spirits, mineral turps or aerosol de-watering agent or lubricant. Do not allow epoxy to harden on equipment.

POINT TO PONDER

Do not thin with solvents, as this will prevent cure. Not intended for repairing cracks subject with movement. Repairs should be made to the cracked member to eliminate the cause of the cracking prior to repair. It is not designed to stop seeping or flowing water. It may be applied in moist or damp environments as long as standing water is removed.

PACKAGING

REC EPO INJECTION 52 is sold in a 600mL dual cartridge.

STORAGE

REC EPO INJECTION 52 has a shelf life of 12 months when stored in the original unopened packaging in a dry place between 13°C and 27°C and 50% relative humidity. If recapped and stored properly, product may be reused.

HEALTH & SAFETY

This product is considered hazardous. Avoid contact with skin and eyes. Wear suitable gloves and eye/face protection. Avoid exposure - obtain special instructions before use. Do not empty into drains. This material and its container must be disposed of in a safe way.

QUALITY STATEMENT

All our products are manufactured to comply with our internal quality management system to ensure consistency and quality.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use. This Data Sheet version is the latest one. The company may modify it without any prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's head office located in Lahore.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd, Lahore. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

WARRANTY: The Reckon Chemicals (Pvt.) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
21 CCA, BLOCK B, KHAYABAN-E-AMIN, LAHORE
Tell: +92-42-35452620, +92-42-35230419
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

