

REC POLYPLAST P015

HIGH PERFORMANCE CONCRETE HYPER PLASTICIZER EXTENDED SLUMP RETENTION

DESCRIPTION

REC POLYPLAST P015 is a highly effective hyper plasticizer based on modified synthetic carboxylated polymers specifically designed to produce ready-mix concrete with low water-to-binder ratio and excellent workability. It can help the ready-mixed concrete industry, where more than normal slump retention and durability are required. The ability to work over a wide range of w/b, including low w/b, and still obtain extended slump retention allows for the manufacturing of high-quality concrete.

PROPERTIES

REC POLYPLAST P015 provides the following properties:

- High water reducing admixture.
- Increased ultimate compressive strength.
- Increased flexural strength.
- Increased durability.
- Superior slump retention. Ease of delivery to point of placement.
- High workability-ease of placing and compaction without segregation.
- Good pumpability - ease of pumping.
- Good workability - excellent surface appearance.
- Minimal bleeding - excellent concrete quality.
- High elastic modulus and high strength - superior load bearing capacity.

SCOPE OF USE

REC POLYPLAST P015 is recommended for all areas of use of high-performance concrete in the ready-mix industry:

- Super slump retaining concrete with equal or less water content than conventional admixtures
- Concrete mixtures containing silica fume, GGBS, or PFA
- Concrete with high resistance against aggressive media
- Long distance transport
- Hot weather concreting
- Highly durable concrete
- Mass concrete
- Pumped concrete
- High strength concrete
- Pervious Concrete
- Sustainable Concrete
- Self consolidating concrete.

TECHNICAL INFORMATION

Appearance	Liquid
Color	Light Brown
Specific gravity at 25°C	1.12 ± 0.03
Chloride content	Nil (BS 5075)
Air Entrainment	Less than 2.0% depending on dosage rate and concrete proportioning.

APPLICABLE STANDARDS:

REC POLYPLAST P015 complies with ASTM C 494 Type D & G, ASTM C1017 Type I & II, BS EN 934, EN 480 & BS 5075.

INSTRUCTIONS FOR USE

REC POLYPLAST P015 should be dispensed after all concrete constituents are charged in the central mixer preferably after approximately 60% of water addition.

DOSAGE

Trials should be conducted to determine the optimum dosage of **REC POLYPLAST P015** for a particular mixture. A dosage of 0.4-2.6% per 100 kg of cementitious material is recommended. Further the required dosage for a specific site with controlled delay in setting and workability should be determined by in-situ trials. In addition, admixture demand varies with w/b of the concrete, cement type, pozzolanic materials and ambient temperature. Trials are to be conducted prior to use in order to determine required performance, including workability retention, setting, and strength development.

EFFECTS OF OVER DOSE

Severe over dose of **REC POLYPLAST P015** will result in the following:

- Delay in initial setting time.
- Increase in air content
- Higher workability
- Impair Consistency and Cohesion.

Dependent upon the level of overdose, concrete mixture details and conditions involved.

COMPATIBILITY

REC POLYPLAST P015 can be used in mixtures containing:

- Silica fume
- Fly Ash
- GGBFS
- Pozzolanic Binders

Consult technical department of Reckon Chemicals for advice.

DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment.

PACKAGING

REC POLYPLAST P015 can be supplied in pails, drums and tanks.

STORAGE

Up to 2 years when stored in accordance with manufacturer's instructions.

HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use. This Data Sheet version is the latest one. The company may modify it without any prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's head office located in Lahore.

NOTE

The information included on this Technical Data Sheet is the sole property of Reckon Chemicals Pvt Ltd, Lahore. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

WARRANTY: The Reckon Chemicals (Pvt) Ltd. (Reckon) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Reckon, no other representations or statements made by Reckon or its representatives, in writing or orally, shall alter this warranty. Reckon MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Reckon product fails to conform with this warranty, Reckon will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Reckon does not authorize anyone on its behalf to make any written or oral statements which in any way alter Reckon's installation information or instructions in its product literature or on its packaging labels. Any installation of Reckon products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Reckon's products for the Buyer's intended purposes.

RECKON CHEMICALS PRIVATE LIMITED
Plot # 6 Km off Manga Road, Glamour Stop,
Opp. Sundar Industrial Estate, Lahore.
Tell: +92-42-35395224-225
Web: www.reckonchemicals.com
Email: Info@reckonchemicals.com

